




207080873



INVESTOR IN PEOPLE

GB 00 / 3799

4




The Patent Office
 Concept House
 Cardiff Road
 Newport
 South Wales
 NP10 8QQ

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.



Signed *Andrew Gersey*

Dated 13 OCT 2000

**PRIORITY
 DOCUMENT**

SUBMITTED OR TRANSMITTED IN
 COMPLIANCE WITH RULE 17.1(a) OR (b)





Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

BEST AVAILABLE COPY

The Patent Office

Cardiff Road
Newport
South Wales
NP9 1RH

1. Your reference

REP06051GBA

2. Patent application number

(The Patent Office will fill in this part)

0009332.8

14 APR 2000

3. Full name, address and postcode of the or of each applicant (underline all surnames)

Freudenberg Ltd.

P.O. Box 3

Ellistones Lane

Greetland

Halifax

West Yorkshire HX4 8NJ

Patents ADP number (if you know it)

If the applicant is a corporate body, give the country/state of its incorporation

United Kingdom

7754237001

4. Title of the invention

NON-WOVEN ABRASIVE MATERIAL

5. Name of your agent (if you have one)

Gill Jennings & Every

"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)

Broadgate House

7 Eldon Street

London

EC2M 7LH

Patents ADP number (if you know it)

745002 ✓

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number

Country

Priority application number
(if you know it)

Date of filing
(day / month / year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application

Date of filing
(day / month / year)

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if:

YES

a) any applicant named in part 3 is not an inventor, or

b) there is an inventor who is not named as an applicant, or

c) any named applicant is a corporate body.

See note (d))

Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form

Description 5

Claim(s) 1

Abstract

Drawing(s)

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (Patents Form 7/77)

Request for preliminary examination and search (Patents Form 9/77)

Request for substantive examination (Patents Form 10/77)

Any other documents (please specify)

NO

11. For the applicant
Gill Jennings & Every

I/We request the grant of a patent on the basis of this application.

Signature

Date

14 April 2000

12. Name and daytime telephone number of person to contact in the United Kingdom

PERRY, Robert Edward

020 7377 1377

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.
- Write your answers in capital letters using black ink or you may type them.
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.
- Once you have filled in the form you must remember to sign and date it.
- For details of the fee and ways to pay please contact the Patent Office.

NON-WOVEN ABRASIVE MATERIAL

Field of the Invention

This invention relates to non-woven abrasive materials.

Background to the Invention

5 Non-woven abrasive materials are well known. They are typically manufactured from polyamide fibres (such as Nylon 6 or Nylon 66), and include a binder such as phenol-formaldehyde (PF) resin.

Most known non-woven abrasive products can be reshaped, in use, by a user, but are unable to maintain that shape. Non-woven abrasive products have
10 been developed that may partially retain a user-defined shape.

Non-woven abrasive materials of the type discussed above are typically sold in pads of a predetermined size. In the alternative, they are sold as rolls; the user may either cut or tear off the required amount, and tearing may be facilitated by the rolls' being perforated at predetermined intervals.

15 US-A-4355067 discloses a fibrous scouring material. US-A-5712210 discloses a non-woven abrasive material roll.

Summary of the Invention

According to a first aspect of the present invention, an abrasive material comprises non-woven, synthetic fibres, and is deformable, and is able to
20 maintain the deformed shape.

According to a second aspect of the present invention, the abrasive material is in the form of a wad of strips.

According to a third aspect of the present invention, a method of manufacturing strips of a non-woven abrasive material comprises the steps of:

- 25 (i) spraying a non-woven fleece with resin and a binder;
(ii) spreading the sprayed fleece with abrasive grains;
(iii) curing the resin; and
(iv) shredding the cured fleece.

A material of the present invention is useful in a number of applications,
30 for example, where a deformable abrasive material is required. Unlike preformed pads or precut rolls, the materials can be used in a variety of forms, as desired, e.g. following pinch extraction from a box or sleeve. In this way, the user may

control the quantity of material dispensed for each application. In particular, the abrasive material can be separated into user-defined quantities.

Advantageously, the wad of abrasive material has a low enough tear strength to allow it to be separated into a smaller wad and a high enough tear strength to maintain its integrity as a wad or deformed wad, when in use.

Description of the Invention

The non-woven abrasive material of the present invention may be manufactured from components typically found in conventional non-woven materials, and by processes similar to those used to manufacture conventional non-woven materials. For example, a method of manufacturing the novel non-woven abrasive material of the present invention may comprise the steps of:

- (i) carding staple fibres;
- (ii) cross-lapping to form a fleece;
- (iii) passing the fleece through a calendar roll;
- (iv) spraying the fleece with resin and a filler binder;
- (v) powder-spreading the fleece with abrasive grain; and
- (vi) heating in a forced air oven to dry and cure the resin.

It will be obvious to one skilled in the art that alternative methods of preparing non-woven abrasive materials are known. For example, air-laying may be used, instead of carding.

A preferred additional step is:

- (vii) shredding the cured fleece to produce strips.

More preferably, the fleece is longitudinally shredded, as this is easier to carry out than transverse shredding of the fleece.

The shredding may produce strips of between 2 and 10 mm width. For example, the strips may be 4 mm wide. However, it is understood that narrower or wider variants may be used to produce the desired effect. It is further understood that any non-woven abrasive material that does not comprise a reinforcing scrim may be shredded.

The material typically has a non-planar structure, in contrast with conventional non-woven abrasive materials. The material can be shaped or "crumpled" into a desired form and has the ability to maintain the crumpled form.

This feature arises from a lower degree of rigidity of the material, as compared with conventional sheets of non-woven abrasive materials, together with a tendency of non-woven abrasive materials to engage with one another.

Non-woven abrasive materials of the present invention may be manufactured from three basic elements. Fibres may be used having a fibre weight of between 30 and 300 g/m². Binders may be used with a binder weight of between 60 and 1000 g/m². Abrasive grains may be used having a weight of between 30 and 600 g/m².

It is understood that any synthetic staple fibre may be used, dependent on the desired use of the product and the binder system employed. Fibre deniers of between 5 and 200, or combinations thereof, may be used, dependent upon the process and also product performance requirements. The fibres typically have staple lengths of about 60 mm. This may vary, dependent on product performance and process requirements.

Abrasives such as aluminium oxide or silicon carbide may be used dependent upon the desired performance characteristics of the product. It is understood that any size, or combination thereof, of abrasive grains may be used, for example, between 36 and 1800 grit.

The following Example illustrates the invention.

20 Example 1

A comparison test was performed on a number of known abrasive products, to illustrate their improved "deformability" after shredding.

Freudenberg products 4223, 4370, 4480, 4650 and 3M Multiflex (™) are commercially available non-woven abrasive materials, manufactured by
25 conventional methods.

For example, 4370 is manufactured from a fibre blend of 90% Nylon 66 60 denier fibre and 10% 20 decitex fibre. The fibres are then blended to ensure that they are evenly distributed.

The blend is opened using a wilying machine and 2 disc openers, and
30 transported by air to the card. The fibres are then processed through the card to produce a uni-directional fleece. The fleece is then passed into a crosslapper to build up layers of fleece, forming a batt of fibre weight 200 g/m². The batt is

then passed through a pair of calender rolls, to reduce its thickness, and then needed.

The fibre batt is sprayed with an aqueous phenol formaldehyde (PF) resin and mineral filler slurry. Included in the slurry is a small percentage (<1% wt) of a pigment. Additional water is added to the slurry, to reduce its solids content and viscosity, allowing it to be sprayed. Prior to spraying, the slurry is about 70% solids. A total of 700 g/m² is sprayed onto the batt. The components making up the slurry are added together to give a total mix weight of about 800 kg. This is continuously agitated, to prevent the solid particles from settling. The ratio of dried resin to filler is 1:3.

The batt is passed through a forced air dryer to dry and cure the resin, and then rolled and cut, as desired. The finished weight is 900 g/m² and it is 12 mm thick.

Additionally, the products were longitudinally shredded to produce thin strips of material, approximately 3.8 mm width.

The following tests have been carried out to quantify the superior "crumpling" properties of the shredded products, compared to the "un-shredded" products.

The product was scrunched up by hand for 3 seconds and allowed to relax on a flat surface for a further 60 seconds. After the recover time had elapsed, the largest and smallest dimensions were measured. This was carried out by placing the sample between two vertical parallel surfaces. The space between the surfaces was altered until the sample was in contact with both surfaces but no deformation of the sample had taken place. The sample was carefully rotated until the maximum dimension was found and measured. The process was repeated to assess the minimum dimension. The products were then shredded and the whole process repeated by scrunching the shredded samples and measuring their dimensions. Table 1 shows the results for the "un-shredded" products. Table 2 shows the results for the shredded products.

It must be noted that prior to shredding the products all had a tendency to expand after scrunching, to a greater or lesser extent. In the main they tried to recover their original flat shape. After shredding the products had a negligible

tendency to expand and remained in the ball-like shape they formed when scrunched.

Table 1

	4223	4370	4480	4650	3M Multiflex (™)
Sample size (cm)	15x22x0.7	15x22x1.2	15x22x1.3	15x22x0.8	15x22x0.4
Largest dimension (cm)	26.6	26.6	26.6	26.6	18.0
Smallest dimension (cm)	0.7	1.2	1.3	0.8	0.4
Largest scrunched dimension (cm)	22.2	21.1	24.3	25.4	14.5
Smallest scrunched dimension (cm)	7.3	8.2	7.7	6.4	5.1
Dimension Ratio	3.04	2.57	3.16	3.97	2.84

Table 2

	4223	4370	4480	4650	3M Multiflex (™)
Sample size (cm)	15x22x0.7	15x22x1.2	15x22x1.3	15x22x0.8	15x22x0.4
Largest dimension (cm)	26.6	26.6	26.6	26.6	18.0
Smallest dimension (cm)	0.7	1.2	1.3	0.8	0.4
Largest shredded dimension (cm)	8.7	9.6	10.9	10.1	6.6
Smallest shredded dimension (cm)	6.4	8.1	8.4	8.5	4.8
Dimension Ratio	1.36	1.19	1.30	1.19	1.38

CLAIMS

1. An abrasive material comprising non-woven, synthetic fibres, which is deformable, and which is able to maintain the deformed shape.
2. An abrasive material according to claim 1, wherein the abrasive is in the form of grains which are held in the material by a resin or other binder.
3. An abrasive material according to claim 2, wherein the grains are of aluminium oxide.
4. An abrasive material according to any preceding claim, in the form of a body which can be separated in user-defined quantities.
5. Strips of an abrasive material according to any of claims 1 to 4.
6. Strips according to claim 5, 2 to 10 mm wide.
7. A wad of strips according to claim 5 or claim 6.
8. A wad according to claim 7, having a low enough tear strength to allow it to be separated into a smaller wad, and a high enough tear strength to maintain its integrity as a wad, when in use.
9. A method of abrading a surface, which comprises contacting the surface with an abrasive material, strips, or wad according to any preceding claim.
10. A method of manufacturing strips of a non-woven, abrasive material, comprising the steps of:
 - (i) spraying a non-woven fleece with resin and a binder;
 - (ii) spreading the sprayed fleece with abrasive grains;
 - (iii) curing the resin; and
 - (iv) shredding the cured fleece.
11. A method according to claim 10, wherein the strips are as defined in claim 5 or claim 6.